

SPECIFICATION SHEET - FOUNDATIONS COLLECTION

Dimensions:	7" Wide x 48.6" Long x 4.2mm thick overall (3.2mm core plus 1mm IXPE pad)
Wear Layer:	12 mil Wear Layer
Finish Coating:	Polyurethane Coating, Embossed
Profile:	4-Sided Painted Bevel
Warranty:	25 Yr Residential, 5 Yr Light Commercial, 5 Yr Multi-Family
Installation:	Tightlock Angle/Drop/Tap



Select Colors Only

TEST METHOD & REQUIREMENTS

	ITEM	TEST METHOD	REQUIREMENT	RESULT
ASTM F3261	Surface Integrity	ASTM F1914	No puncture	Pass
	Dimensional Stability	ASTM F2199/ISO 23999	$\Delta W/\Delta L \leq 0.2\%$ (commercial)	Pass
	Curling	ASTM F2199/ISO 23999	$\leq 2\text{mm}$	Pass
	Length tolerance	ISO 24337	$\pm 2\text{ mm}$	Pass
	Width tolerance	ISO 24337	$\pm 0.4\text{mm}$	Pass
	Thickness tolerance	ASTM F387	$\pm 0.13\text{mm}$ (no backing); $\pm 0.20\text{mm}$ (with)	Pass
	Squareness	ISO 24337	0.25mm	Pass
	Flatness	ISO 24337	Length: $\leq 0.50\%$ (concave) $\leq 1.0\%$ (convex) Width: $\pm 0.008\text{ in.}$ (0.2mm) for planks or tiles $\leq 9\text{ in.}$ (229mm) wide	Pass
	Residual Indentation	ASTM F1914	$\leq 0.18\text{mm}$ (70lbs/34kg)	Pass
	Static load	ASTM F970/ASTM F387	$\leq 0.13\text{mm}$	Pass
	Resistance to chemicals	ASTM F925	Slight change only	Pass
	Resistance to Heat	ASTM F1515	$\Delta E \leq 8$	Pass
	Resistance to light	ASTM F1514	$\Delta E \leq 8$	Pass
	ASTM F1700*	Residual Indentation	ASTM F1914	$\leq 8\%$ (140 lbs/63.5kg)
Dimensional Stability		ASTM F2199	$\Delta W/\Delta L \leq 0.16\%$	Pass
ISO 10582	Resistance to light	ISO 105-B02:1994 Method 3A	$\geq \text{Grade 6}$	Pass
	Locking strength	ISO 24334	$\geq 1.5\text{ kN/m}$	Pass
	Castor chair	ISO 4918	Only slight change	NA
NALFA LF 01-2011	Resistance to Chemicals	NALFA LF 01-2011	Slight change only	Class 4, meets commercial requirements
	Impact Resistance	NALFA LF 01-2011 3.5	$\geq 1400\text{mm}$	Class 4, meets commercial requirements
	Impact Resistance	NALFA LF 01-2011 3.6	$\geq 500\text{mm}$	Class 4, meets commercial requirements
EN 14041	Thermal Resistance (R)	EN 12667/ASTM C518	NA	Suitable for underfloor heating systems
	Slipperiness	EN 13893	≥ 0.3	Pass
	Reaction to fire	EN 13051-1	NA	Class Bfl -S1
	Static Electrical Propensity	EN 1815 (voluntary)	$\leq 2.0\text{kV}$	NA
Others	Density	ISO 23996	NA	Around 1580kg/m ³
	Airborne sound transmission	ASTM E413-16	≥ 50	STC 69
	Impact sound transmission	ASTM E989-6	≥ 50	IIC 69
	Reducing impact sound transmission	ASTM E2190-16	NA	Delta IIC 23
	SCOF	ASTM D2047	> 0.5	Pass
	Slipperiness	DIN 51130	NA	R10
Fire Resistance (CHF)	ASTM E648/NFPA 253	≥ 0.45	Pass	

*Note: Only tests specific to ASTM F1700 are listed here; for tests and requirements similar to ASTM F3261, please refer to the tests under that standard. LEED and WELL Scorecards available upon request